

## EWP 215 – Sealing material for intake manifold, water and fuel pumps, oil pan and housing cover



### Description

Gasket material, based on aramide fibers with NBR binder. Excellent oil and fuel resistance combined with good stress relaxation and high tensile strength.

### Technical data

Thickness	≤ 0,5 mm	≥ 0,5 mm
Density DIN 53105 Tl. 1	1,65 g/cm <sup>3</sup> ± 0,1	1,65 g/cm <sup>3</sup> ± 0,1
Ignition loss DIN 52911	≤ 38%	≤ 38%
Compressibility ASTM F36 J	9% ± 4	9% ± 4
Recovery ASTM F36 J	≥ 45%	≥ 45%
Tensile strength, cross grain, DIN 52910	≥ 12 N/mm <sup>2</sup>	≥ 12 N/mm <sup>2</sup>
Stress relaxation DIN 52913 (50 N/mm <sup>2</sup> , 16 h/300°C)		≥ 22 N/mm <sup>2</sup>
Media resistance		
ASTM Oil no. 3 (5 h/150°C)		
Thickness increase	≤ 10%	≤ 10%
Weight increase	≤ 15%	≤ 15%
ASTM-Fuel B (5 h/23 ± 2°C)		
Thickness increase	≤ 12%	≤ 12%
Weight increase	≤ 15%	≤ 15%
Wasser – Glykol (1:1, 5 h Rf)		
Thickness increase	≤ 10%	≤ 10%
Weight increase	≤ 17%	≤ 17%

# Elring EWP 215



Das Original

## **Application**

EWP 215 is primarily used as sealing against cold and hot oils, fuels and coolants with corrosion inhibitors and antifrost additives.

Typical applications are intake manifold, water and fuel pump, oil pan and housing cover.

Color	green
Max. temperature	400°C (in oil max. 200°C)
Max. pressure	100 bar

## **Form of supply**

EWP 215 can be supplied as a ready to install gasket according to drawing or as a sheet product.



**Das Original**

**ElringKlinger AG** | Aftermarket Division  
Max-Eyth-Straße 2 | D-72581 Dettingen/Erms  
Phone ++49 (0)71 23/724-622 | Fax ++49 (0)71 23/724-609  
elring@elring.de | www.elring.de