

Proven products even better: the Elring sealant range



	Curil™ T2	Curil™ T2 ProfiPress	Dirko™ HT	Dirko™ HT	Dirko™ HT	Dirko™ HT ProfiPress	Dirko™ HT	Dirko™	EL-Liq 73	EL-Liq 74	EL-Loc 43	EL-Loc 70	EL-Add 48	EL-FIL 77
Item no. Package size	471.081 70 ml 252.869 500 ml	471.181 200 ml	036.164 70 ml 610.023 310 ml	030.793 70 ml	006.553 70 ml	471.501 200 ml	705.708 70 ml 465.766 310 ml	216.910 310 ml	777.792 50 ml	461.682 50 ml	700.501 10 ml 954.000 50 ml	700.521 10 ml 954.010 50 ml	954.030 50 ml	954.020 50 ml
Colour	green	green	grey	beige	black	black	red	transparent	yellow/green	orange	blue	turquoise green	green	yellow
Application	surface sealing	surface sealing	gap sealing/ surface sealing	gap sealing/ surface sealing	gap sealing/ surface sealing	gap sealing/ surface sealing	gap sealing/ surface sealing	gap sealing/ surface sealing	medium-strength surface sealing	medium-strength surface sealing	screw lock	screw lock	joining	pipe thread sealing
Curing	none, permanently plastic	none, permanently plastic	humidity	humidity	humidity	humidity	humidity	humidity	air exclusion + metal contact	air exclusion + metal contact	air exclusion + metal contact	air exclusion + metal contact	air exclusion + metal contact	air exclusion + metal contact
Maximum sealing gap	≤ 0.2 mm	≤ 0.2 mm	≤ 2.0 mm	≤ 2.0 mm	≤ 2.0 mm	≤ 2.0 mm	≤ 2.0 mm	≤ 2.0 mm	≤ 0.20 mm	≤ 0.25 mm			≤ 0.20 mm	
Thread size											≤ M36	≤ M20		≤ M80
Temperature range	-55 °C bis +270 °C	-55 °C bis +270 °C	-60 °C bis +315 °C	-60 °C bis +315 °C	-60 °C bis +315 °C	-60 °C bis +315 °C	-60 °C bis +315 °C	-60 °C bis +250 °C	-55 °C bis +180 °C	-55 °C bis +180 °C	-55 °C bis +180 °C	-55 °C bis +180 °C	-55 °C bis +180 °C	-55 °C bis +180 °C
Metal-metal surface	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Metal-plastic surface	X	X	X*	X*	X*	X*	X*	X*						
Plastic-plastic surface	X	X	X*	X*	X*	X*	X*	X*						
Oil resistant	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Fuel resistant	X	X							X	X	X	X	X	X
Coolant resistance	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Viscosity									●	●	●●	●●●	●●●	●
Recommissioning after	immediate	immediate	approx. 30 min	approx. 30 min	approx. 30 min	approx. 30 min	approx. 30 min	approx. 30 min	3 – 6 h	3 – 6 h	3 – 6 h	3 – 6 h	3 – 6 h	3 – 6 h
Removal	very easy	very easy												
Removal of old sealant	cleaner, cloth	cleaner, cloth	scraper, brush, cleaner, cloth	scraper, brush, cleaner, cloth	scraper, brush, cleaner, cloth	scraper, brush, cleaner, cloth	scraper, brush, cleaner, cloth	scraper, brush, cleaner, cloth	hot air 250 °C brush, cleaner, cloth	hot air 250 °C brush, cleaner, cloth	hot air 250 °C brush, cleaner, cloth	hot air 250 °C brush, cleaner, cloth	hot air 250 °C brush, cleaner, cloth	hot air 250 °C brush, cleaner, cloth

* Plastics except PP, PE, PTFE, EPDM, APTK, neoprene, butyl, foam | ● = high viscosity, viscous | ●● = medium viscosity | ●●● = low viscosity, runny

The information specified here has been compiled with the utmost care based on many years of experience. However, no guarantee can be provided as success is only ensured if the specific circumstances of each individual situation are taken into account.



Online sealant adviser:
Find the right product in 3 steps



Any more questions?
You can find further information
in our sealant FAQs

C500088 0724 EN

Elring service hotline
+49 7123 724-799
service@elring.com
www.elring.com

